

Ancaster Hard White

Quarry Location:

Ancaster Quarry
Quarry Farm
Ancaster, Nr Grantham
Lincolnshire, England



Technical Results

Description	Fine-grained Jurassic Limestone Durable with good weathering qualities	
Country of Origin	UK	
Geological Type	Jurassic Limestone	
Colour	Cream White / Occasional Pink variation	
Density	2299 kg/m ³	
Compressive Strength	25 MPa	BS EN 1926 (1999)
Water Absorption	10.59% by mass	BS EN 13755 (2002)
Porosity	25.14%	BRE 141
Durability	Pass Change in flexural strength 14.0%	BS EN 1341 (2001)
Slip Resistance	Dry 67 Wet 41	BS EN 1341 (2001)
Abrasion Resistance	25.4mm Moderate commercial use	BS EN 1341 (2001)
Flexural Strength	8.17 MPa	
Saturation co-efficient	0.86	BRE 141
Average Block Size	1500L x 1000W x 300H	

Sales:

Block Stone Limited
Grant House
Prospect Way
Hutton
CM13 1XD

Tel: +44 (0) 1246 554450

Email: sales@blockstone.com

www.blockstone.com

Please note that stone is a natural product and all results are subject to variation