

**Quarry Location:**  
Wattscliffe Quarry,  
Cliffe Lane, Elton,  
Derbyshire, UK



### Technical Results

<b>Description</b>	Medium Grained Sandstone Durable with good weathering qualities	
<b>Country of Origin</b>	UK	
<b>Geological Type</b>	Carboniferous / Millstone Grit	
<b>Colour</b>	Lilac / Grey	
<b>Density</b>	2260 kg/m <sup>3</sup>	
<b>Compressive Strength</b>	56 MPa	BS EN 1926 (1999)
<b>Water Absorption</b>	4.75%	BS EN 13755
<b>Porosity</b>	14.70%	BS EN 1936 (1999)
<b>Durability</b>	Durability tests indicate that failure due to frost action is unlikely	
<b>Saturation co-efficient</b>	0.67%	BRE 89
<b>Acid Immersion</b>	Pass	BRE 141
<b>Average Block Size</b>	2000L x 1000W x 1000H	
<b>Additional Test</b>	Flexural Strength (3-point) 5.1 MPa	BS EN 12372 (2006)

Please note that stone is a natural product and all results are subject to variation

**Sales:**  
Block Stone Limited  
Grant House  
Prospect Way  
Hutton  
CM13 1XD

**Tel:** +44 (0) 1246 554450  
**Email:** sales@blockstone.com

[www.blockstone.com](http://www.blockstone.com)