BLOCKSTONE

Mine Location: Park Lane Mine Brockleaze Neston Corsham SN13 9TW Wiltshire England

Sales: Block Stone Limited Grant House Prospect Way Hutton CM13 1XD

Tel: +44 (0) 1246 554450 **Email:** sales@blockstone.com

www.blockstone.com

Park Lane Bathstone Top Bed



Technical Results

| Description | Cream limestone; uniform with some calcite veins | |
|-------------------------------|--|------------|
| Country of Origin | UK | |
| Geological Type | Oolitic Limestone | |
| Colour | Warm Honey/cream | |
| Density | 2000 kg/m³ | BSEN 1936 |
| Compressive Strength | 23MPa | EN772-1 |
| Water Absorption at | 11.7% by mass | BSEN 13755 |
| atmospheric pressure | | |
| Open Porosity | 25.6% | BS EN 1936 |
| | | |
| Flexural Strength under conc. | 3.4 MPa perpendicular to bed | BSEN 12372 |
| load: | | |
| Average Block Size | 1500L x 1000W x 700H | |
| Saturation coefficient | 0.87 | BRE 141 |

Please note that stone is a natural product and all results are subject to variation